

Report No.:

248105417-01

Client:

BECKER CHEM PAINTS JOINT STOCK COMPANY

Contact Information:

Danh Hamlet, Minh Duc Ward, Viet Yen District, Bac Giang Province,
Vietnam

Test item(s):

Coated Wood

Identification/

PU White; Model: Acacia Wood painted White; Material: Paint; Color:

Model No(s):

White

Sample Receiving date:

2019-08-08

Testing Period:

2019-08-08 to 2019-08-20

Test Specification:


Test result:

Test parameter chosen by customer:

1. Accelerated weathering test - Methods Of Exposure To Laboratory Light
Sources - Xenon-Arc Lamps

Please refer result to
page 2

For and on behalf of
TÜV Rheinland Vietnam Co., Ltd.




2019-08-20

Dao Thuy Khanh Linh / Project Manager

Date

Name/Position

Test result is drawn according to the kind and extent of tests performed.
This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be
duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.

TÜV Rheinland Vietnam Co., Ltd. Laboratory: 1st Floor, Block No.10, Street No.4, Quang Trung Software City District 12 Ho Chi Minh City
Tel.: + 84 28 3715 4025 · Fax: + 84 28 3715 4028 · E-mail: info@vn.tuv.com · Web: www.tuv.com/vn

Test Report No.: 248105417-01

Page 2 of 3

Material List:

Item: PU White; Model: Acacia Wood painted White; Material: Paint; Color: White

Material No.	Material	Color	Location
M001	Coated wood	White	Coated wood

1. Accelerated weathering test - Methods Of Exposure To Laboratory Light Sources - Xenon-Arc Lamps

Test method : Methods Of Exposure To Laboratory Light Sources - Xenon-Arc Lamps (ISO 4892-2: 2016; Assessment according to ISO 105-A02: 1993)

Exposure : Exposed to xenon-arc lamp, cycle 4

M001

After 200 hrs


Colour change 4-5

Remark : Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good

Test Report No.: 248105417-01

Page 3 of 3

Sample Photo



Lab.ID.: A000971310-001

- END -